

Test Report

No. SH8022128/ CHEM

Date: Mar. 20, 2008

Page 1 of 5

公司名称: 上海宝山钢铁股份有限公司

Company Name: SHANGHAI BAOSHAN IRON & STEEL CO., LTD

地址: 上海同济路 1800 号

Address: 6/F, 1800 TONGJI RD, BAOSHAN, SHANGHAI, CHINA

样品名称: 电镀锡普板

TYPE OF PRODUCT: ELECTROLYTIC TINPLATE

SGS 相关号: 10869348-3

SGS Ref No.: 10869348-3

收件日期(SAMPLE RECEIVED). Feb.27, 2008

测试日期(TESTING DATE). Feb.27 to Mar.01, 2008 Mar.17 to 20, 2008

- Test Requested/测试要求 : (1) To determine the Cadmium, Lead and Mercury content of the electroplating for submitted sample.
测定委托样品电镀层中镉, 铅, 汞的含量
- (2) To determine the Hexavalent Chromium content of the electroplating for submitted sample.
测定委托样品电镀层中六价铬的含量
- (3) To determine the PFOS (Perfluorooctane Sulfonates) and PFOA (Perfluorooctanoic Acid) content of the electroplating for submitted sample.
测定委托样品电镀层中全氟辛烷磺酰基化合物(PFOS) 和全氟辛酸(PFOA)的含量

试验方法/测试结果 : 见后续页

Test method/Test Results: Please refer to next page

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Ella Zhang
Section Manager

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Sandy Hao
Lab Manager

Test Report

No. SH8022128/ CHEM

Date: Mar. 20, 2008

Page 2 of 5

Test method/测试方法

- : (1) Acid washing method for Cadmium, Lead and Mercury content in electroplating.
 Analysis was performed by Inductively Coupled Argon Plasma-Atomic Emission Spectrometer (ICP-AES) and Atomic Absorption Spectrometer (AAS).
 酸洗脱方法测定电镀层中的镉,铅和汞含量.
 采用ICP和AAS进行分析
- (2) With reference to IEC 62321/2nd CDV (111/95/CDV) for Hexavalent Chromium by spot test / Colorimetric Method.
 参照 IEC 62321/2nd CDV (111/95/CDV), 采用点测试法/比色法测定六价铬的含量
- (3) With reference to EPA 3550C: 2000.
 Analysis was performed by High Performance Liquid Chromatograph-Mass Spectrometer (HPLC-MS).
 参照 EPA 3550C: 2000 方法. 采用 HPLC-MS 测试.

Test results by chemical method

(1)-(2) Cadmium, Lead, Mercury and Hexavalent Chromium content of the electroplating for submitted sample.

(Unit: mg/kg)

样品电镀层中镉, 铅, 汞和六价铬的含量(单位: mg/kg)

<u>Test Item(s)/</u> <u>测试项目</u>	<u>Method(refer to)/</u> <u>方法(参见)</u>	<u>1</u>	<u>MDL</u>
Cadmium (Cd) in electroplating/ 电镀层中镉(Cd)	(1)	ND	10
Lead (Pb) in electroplating/ 电镀层中铅(Pb)		ND	10
Mercury (Hg) in electroplating/ 电镀层中汞(Hg)		ND	10
Hexavalent Chromium (Cr VI)/ 六价铬(Cr VI)	(2)	Negative	See Note (4)/ 参见备注 (4)

(3) PFOS (Perfluorooctane Sulfonates) and PFOA (Perfluorooctanoic Acid) content of the electroplating for submitted sample (Unit: ug/m²)

样品电镀层中全氟辛烷磺酰基化合物(PFOS) 和全氟辛酸(PFOA)的含量(单位: ug/m²)

Test Item(s)/ 测试项目	Method(refer to)/ 方法(参见)	1	MDL
PFOS (Perfluorooctane Sulfonates) $\Sigma \left\{ \begin{array}{l} \text{PFOS-acid} \\ \text{PFOS-salt} \end{array} \right\}$ 全氟辛烷磺酰基化合物(PFOS) $\Sigma \left\{ \begin{array}{l} \text{PFOS-酸} \\ \text{PFOS-盐} \end{array} \right\}$	(3)	ND	1
PFOA(Perfluorooctanoic Acid) $\Sigma \left\{ \begin{array}{l} \text{PFOA-acid} \\ \text{PFOA-salt} \end{array} \right\}$ 全氟辛酸(PFOA) $\Sigma \left\{ \begin{array}{l} \text{PFOA-酸} \\ \text{PFOA-盐} \end{array} \right\}$		ND	1


Test Part Description:

1. Silvery metal board

Note :

- (1) mg/kg=ppm
毫克每千克=百万分之一(mg/kg=ppm)
- (2) ND = Not detected
ND=未检出
- (3) MDL = Method Detection Limit
MDL =检测极限值
- (4) Spot-test:
Negative = Absence of CrVI coating, Positive = Presence of CrVI coating;
(The tested sample should be further verified by boiling-water-extraction method if the spot test result is Negative or cannot be confirmed.)
Boiling-water-extraction:
Negative = Absence of CrVI coating
Positive = Presence of CrVI coating; the detected concentration in boiling-water-extraction solution is equal or greater than 0.02 mg/kg with 50 cm² sample surface area.
点测试法:
Negative= 镀层中未检测到六价铬, Positive = 镀层中检测到六价铬;
(当点测试结果为 Negative 或无法确定时,将采用沸水萃取法作进一步的结果验证。)
沸水萃取法:
Negative = 镀层中未检测到六价铬
Positive = 镀层中检测到六价铬; 表明 50 cm² 表面积的被测试样品的沸水萃取液中六价铬的浓度等于或大于 0.02 mg/kg

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***