

Test Report

No. SH8063072/ CHEM

Date: May. 13, 2008

Page 1 of 3

公司名称: 上海宝山钢铁股份有限公司

Company Name: SHANGHAI BAOSHAN IRON & STEEL CO., LTD

地址: 上海同济路 1800 号

Address: 6/F, 1800 TONGJI RD, BAOSHAN, SHANGHAI, CHINA

样品名称: 电镀锌耐指纹

TYPE OF PRODUCT: CONTINUOUSLY ELECTROLYTIC ZINC COATED

STEEL, ANTIFINGER TREATMENT WITHOUT HEXAVALENT CHROMUM

SGS 相关号: 11012131-6

SGS Ref No.: 11012131-6

收件日期(SAMPLE RECEIVED): May. 07, 2008

测试日期(TESTING DATE): May. 07 to 12, 2008

Test Requested/测试要求 : (1) To determine Cobalt content in the submitted sample .
测定委托样品的钴含量.

试验方法/测试结果 : 见后续页

Test method/Test Results: Please refer to next page

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Ella Zhang
Section Manager

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Sandy Hao
Lab Manager

Test Report

No. SH8063072/ CHEM

Date: May. 13, 2008

Page 2 of 3

Test method/测试方法 : (1) HNO₃/HCl acid digestion for Cobalt content for sample . Analysis was performed by ICP.
 (1) 硝酸/盐酸消解测定样品中的钴含量.
 采用 ICP 进行分析.

Test results by chemical method
 化学方法试验结果

<u>Test Item(s)</u> 测试项目	<u>1</u>	<u>Unit</u> 单位	<u>MDL</u>
Cobalt (Co)/ 钴(Co)	11	mg/kg	2


Test Part Description:

1. Silvery metal board

Note :

- (1) mg/kg=ppm
毫克每千克=百万分之一(mg/kg=ppm)
- (2) MDL = Method Detection Limit
MDL =检测极限值

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***